

# TIG Consumables

## T-2209

For duplex stainless steels (Low carbon, 22%Cr-9%Ni-Mo STS)

### Classifications

EN ISO 14343-A:2009

: W 22 9 3 N L

EN ISO 14343-B:2009

: SS 2209

AWS A5.9-15

JIS Z 3321:2013

: ER2209

: YS2209

### Description

- TIG welding of 22%Cr-9%Ni-3%Mo duplex stainless steels (UNS S31803, STS 329J1, 329J2L)
- A various application of the petrochemical offshore structure and distilling apparatuses.

### Typical chemical composition of wire (%)

C	Si	Mn	Ni	Cr	Mo
0.01	0.40	1.67	8.70	22.70	3.10

### Typical mechanical properties of all-weld metal

	Y.S (MPa)	T.S (MPa)	EI. (%)	-10°C	IV (J) -50°C
AWS A5.9		min. 690	min. 20		
EN ISO 14343	min. 450	min. 550	min. 20		
Example	769	855	32	183	160