

# T-309LSi

For austenite stainless steel (Low carbon, Dissimilar steels)

## Classifications

EN ISO 14343-B:2009

: SS 309LSi

JIS Z 3321:2013

: YS309LSi

AWS A5.9-2012

: ER309LSi

## Description

- TIG welding of 22%Cr-12%Ni STS and dissimilar steels such as 304L to mild steels or low alloy steels.
- A various application of petrochemical and fiber industrial apparatuses.

## Typical chemical composition of wire (%)

C	Si	Mn	Ni	Cr
0.01	0.91	1.86	13.62	23.07

## Typical mechanical properties of all-weld metal

	Y.S (MPa)	T.S (MPa)	EI. (%)	IV (J) 0°C
AWS A5.9		min. 520	min. 30	
EN ISO 14343	min. 320	min. 510	min. 25	
Example	410	520	42	120