



Elgatig 100

GTAW - TIG
Un-alloyed

Date: 2020-09-18
Revision: 8

Description:

Elgatig 100 is a silicon, manganese double deoxidised welding wire suitable for high integrity TIG welding of mild and medium tensile steels. It is recommended for Si-killed materials.

Welding current:

DC-

Wire composition, wt. %

	C	Si	Mn	P	S	Cu
Min	0,07	0,80	1,40			
Typical	0,08	0,90	1,50	0,010	0,015	
Max	0,14	1,00	1,60	0,025	0,025	0,30

Shielding gas:

I1, Argon, 7-10 l/min

Stamping

F ER70S-6

Chemical composition, wt. %

	C	Si	Mn
Min			
Typical	0,07	0,9	1,4
Max			

Mechanical properties

	<u>Specified</u>	<u>Typical</u>
Yield strength, Re:	≥ 460 MPa	480 Mpa
Tensile Strength, Rm:	≥ 530 - 680 Mpa	580 Mpa
Elongation, A5	≥ 22%	26%
Impact energy, CV:	-50°C • >47 J	-50°C • 60 J

Classification:

EN ISO 636-A W 46 5 W3Si1
AWS A5.18 ER70S-6

Approvals:

DB Kennblatt Nr 42.042.03
TÜV
CE

Product data:

Ø x Length mm	Packet weight
1,6 x 1000	5 kg
2,0 x 1000	5 kg
2,4 x 1000	5 kg
3,0 x 1000	5 kg

*The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and ITW Welding AB expressly disclaims any liability incurred from any reliance thereon. Typical data are those obtained when welded and tested in accordance with the corresponding EN ISO specification. Other tests and procedures may produce different results. No data is to be construed as a recommendation for any welding condition or technique not controlled by ITW Welding AB.

ITW Welding reserves the right to change specifications or approvals without prior notice.